

Definition / Tanımlama

PURINAQUA IC 104 Polycarbonate is a polyol based anionic polyurethane dispersion. Since it is an aliphatic resin, it does not yellow with UV light.

Application Area / Uygulama Yeri

PURINAQUA IC 104 Polycarbonate is a polyol-based polyurethane dispersion with excellent hydrolysis resistance, strong acid-base resistance, excellent mechanical resistance and strong water repellency, and is used for coating in many areas such as wood, metal, construction, packaging and textiles.

Advantages / Avantajlar

- UV non-yellowing with aliphatic structure
- Adjustable to the desired viscosity
- Environmentally friendly product with water-based structure
- Strong water repellency
- High performance contribution
- Clean, odor-free working environment
- Long application time
- Short drying time
- Long shelf life and stock period
- Application equipment and areas can be cleaned with water
- Non-hazardous, non-flammable

Technical Properties / Teknik Özellikler

No	Test / Analiz	Result / Sonuç	Unit / Birim	Test Code
1	Appearance	White - Blue	-	
2	Viscosity	1.000 - 2.000	cP (23°C)	ASTM 2196
3	Density	1,00 - 1,05	g/cm3 (23°C)	ISO 2811
4	Solid content	30-32	%	ISO 3251
5	Elongation at break	300-400	%	ASTM D 412
6	Modulus of elongation	97,50	N/mm2	ASTM D 412
7	Maximum tension	19,50	N/mm2	ASTM D 412
8	Hardness	40	Shore D	ASTM D 2240

Preparation / Hazırlık

If the product is to be modified, it is formulated with the necessary additives and auxiliary resins. The performance of the formulated product must be tested beforehand. Because the formulated product will not be the same as the performance of PUD resin.

In addition, the usage period of the formulated products should be determined and all of them should be used within this period. When formulating, water-based crosslinkers can be used to increase the properties of the system if necessary. It is suitable for direct use or diluted with water for dipping system

Application / Uygulama

The product is applied by dipping, roller, spray, roller or brush depending on the application area, and then it should be taken to drying process.

The drying process can be natural drying or oven or hot air drying. In the drying process with heat, the preheat is first given at 70-80oC and then it should be increased to 105-120oC since high heat will cause the product to swell.

Cleaning / Temizlik

The product is applied by dipping, roller, spray, roller or brush depending on the application area, and then it should be taken to drying process.

The drying process can be natural drying or oven or hot air drying. In the drying process with heat, the preheat is first given at 70-80oC and then it should be increased to 105-120oC since high heat will cause the product to swell.

Packing / Paketleme

The product is packed and shipped in IBC tanks as 1.000kg or in plastic drums as 20kg-60kg.



Storage / Depolama

Its service life is 12 months from the date of production in its unopened original packaging, in a dry environment, protected from direct sunlight and frost.

Safety and Health / Güvenlik ve Sağlık

Avoid contact with skin and eyes. In case of contact, rinse with plenty of water. In case of irritation, consult a doctor immediately.

Note

The information on this data sheet is based on our experiences and correct to the best of our knowledge. It is, however, not binding. It has to be adjusted to the individual structure, application purpose and especially to local conditions. Our data refers to the accepted engineering rules, which have to be observed during application. This provided we are liable for the correctness of this data within the scope of our terms and conditions of sale-delivery-and-service. Recommendations of our employees which differ from the data contained in our information sheets are only binding if given in written form. The accepted engineering rules must be observed at all times.

Bu teknik formdaki veriler kendi deneyimlerimiz ve bilgilerimiz referans alınarak hazırlanmıştır. Ancak bağlayıcılığı yoktur. Yapıya, uygulama amacına ve özellikle yerel koşullara göre ayarlanmalıdır. Verilerimiz, uygulama sırasında uyulması gereken mühendislik kurallarını referans almıştır. Satış teslim, hizmet şartlarımız ve koşullarımız kapsamında bu verilerin doğruluğundan sorumlu olmaktayız. Çalışanlarımızın bilgilendirme formlarımızdaki yer alan verilerden farklı önerileri ancak yazılı olarak verilmesi halinde bağlayıcıdır. Kabul edilen mühendislik kurallarına her zaman uyulmalıdır.

**PURIN®Aqua****PURIN®ATE****PURIN®COAT PURIN®ADHE PURIN®SEAL PURIN®ELAS**